

NBE7200G30



測試項目	Testing Item	ASTM	單位 Unit		數值 Value
抗張強度	Tensile strength	D-638	Kg/cm ²		1400
延伸率	Tensile elongation	D-638	%		5.0
抗折強度	Flexural strength	D-790	Kg/cm ²		2400
抗折模數	Flexural modulus		Kg/cm ²		70000
衝擊強度	Izod impact (1/8", V-notched)	D-256	Kg · cm / cm (23°C) (-30°C)		18.0 -
熱變形溫度	Heat distortion temperature	D-648	°C (18.6Kg/cm ²)		200
熔融溫度	Melting point	DSC	°C		250~260
硬度	Hardness	D-785	Rockwell R		116
模縮率	Mold shrinkage	D-955	flow direction	%	0.3
			perpendicular direction	%	0.7
比重	Specific gravity	D-792	-		1.32
灰份	Ash content	D-482	%		30(GF)
耐燃性	Flammability	UL-94	1/16"		-

尼龍 66, 超韌耐衝擊 30%玻纖增強黑色

NYLON 66, Glass fiber 30% reinforced, super high impact,
black colored.

預處理條件：23°C, 50%RH, 24 小時

Pretreatment : 23°C, 50%RH, 24hrs