

NB2210Mo3



測試項目	Testing Item	ASTM	單位 Unit		數值 Value
抗張強度 延伸率	Tensile strength	D-638	Kg/cm ²		800
	Tensile elongation	D-638	%		4.0
抗折強度 抗折模數	Flexural strength	D-790	Kg/cm ²		1400
	Flexural modulus		Kg/cm ²		32000
衝擊強度	Izod impact (1/8", Un-notched)	D-256	Kg · cm / cm		30.0
			(23°C) (-30°C)		-
熱變形溫度	Heat distortion temperature	D-648	°C (18.6Kg/cm ²)		220
熔融溫度	Melting point	DSC	°C		250~260
硬度	Hardness	D-785	Rockwell R		119
模縮率	Mold shrinkage	D-955	flow direction	%	1.0
			perpendicular direction	%	2.0
比重	Specific gravity	D-792	-		1.16
灰份	Ash content	D-482	%		-
耐燃性	Flammability	UL-94	1/16"		-

尼龍 66, 耐磨耗性
 NYLON 66, anti-abrasion.

預處理條件：23°C, 50%RH, 24 小時
 Pretreatment : 23°C, 50%RH, 24hrs