



CA6472B

測試項目	Testing Item	ASTM	單位 Unit		數值 Value
抗張強度	Tensile strength	D-638	Kg/cm ²		550
延伸率	Tensile elongation	D-638	%		40.0
抗折強度	Flexural strength	D-790	Kg/cm ²		1000
抗折模數	Flexural modulus		Kg/cm ²		25000
衝擊強度	Izod impact (1/8", V-notched)	D-256	Kg · cm / cm (23°C) (-30°C)		60.0 -
熱變形溫度	Heat distortion temperature	D-648	°C Unannealed		95
流動指數	Melt index	D-1238	g/10min (260°C/3.80kg) (275°C/2.16kg)		10.0 -
硬度	Hardness	D-785	Rockwell R		110
模縮率	Mold shrinkage	D-955	flow direction	%	0.4
			perpendicular direction	%	0.7
比重	Specific gravity	D-792	-		1.13
灰份	Ash content	D-482	%		-
耐燃性	Flammability	UL-94	1/16"		HB

PC/ABS 鈐金 一般用途黑色

PC/ABS Alloy General purpose, black colored.

預處理條件：23°C, 50%RH, 24 小時

Pretreatment : 23°C, 50%RH, 24hrs